

TECHNICAL INFORMATION

FOR PROFESSIONAL USE ONLY

RANGERS

2K polyurethane protective coating

3:1

PRODUCTS

RANGERS 3:1- 2K polyurethane protective coating.
Hardener for RANGERS 1:3.
ZERO VOC Thinners for acrylic systems TROTON.

PRODUCT DESCRIPTION

2-component polyurethane protective Coatings with structure effect. Tough coating offers great chemical resistance against oil, gasoline, water and salt; as well as mechanical resistance against scratches and stains. High performance formulation contains UV Filters and anticorrosive additives that effectively protect against extreme climatic conditions, color fading, rust and corrosion. Can be applied on various substrates with an UBS antigravel gun or any conventional gravity feed spray gun.

- ✓ Tough durable coating
- ✓ Great chemical and mechanical resistance
- ✓ Soundproofing properties
- ✓ Anti-slip structure

VOLATILE ORGANIC COMPOUNDS

VOC = 2.1 lbs/gal




SUBSTRATES AND PREPARATION

- ✓ Do not apply the product directly on bare metal. Rangers should be applied on primed surfaces or on 2K topcoats and basecoats after proper preparation (be careful with the application on old coatings, thinner testing is advised).
- ✓ Always abrade, clean and degrease the surface before application.
- ✓ Do not apply the product on 1K primers. Instead, always prime the surfaces for the Rangers application with a 2k acrylic primer, 2K epoxy primer or 2k etching primer.
- ✓ Always wait the proper drying and hardening time of etching primer before application.
- ✓ Do not apply Rangers directly on bare original paint or directly on coatings of car body parts from the aftermarket.


Substrates:

- Steel, galvanized steel, stainless steel, aluminum – prime surfaces with a 2K epoxy primer or 2K acrylic primer, sand using abrasive paper with gradation from P180 to P320, clean and degrease (Silicone Remover Troton).
- Polyester laminates – sand using abrasive paper P180 or by using Troton’s unwoven abrasive fabric, clean and degrease (Silicone Remover Troton).
- Polyester body fillers - sand using abrasive paper with gradation from P120 to P240, clean and degrease (Silicone Remover Troton).
- Plastic surfaces - degrease (Silicone Remover Troton), sand with abrasive paper P240 or with Troton’s unwoven abrasive fabric, degrease again (Silicone Remover Troton), prime with an adhesive promoter, such as Plastic Primer Troton. Due to the many different types of plastic, adhesion testing is advised.

APPLICATION PROCESS RANGERS black / tintable


UBS Gun	
	<p>Proportion ratio:</p> <p>3:1 By volume: 600ml +200ml By weight: 803g+243g</p> <p>Shake the product before opening. Open the lid, add hardener and close back the lid. Shake very well.</p>
	<p>Pot life</p> <p>About 1 h at 20°C (68°F)</p>
	<p>Number of layers</p> <p>2 layers. 1 dry layer of approx. 150µm.</p> <ol style="list-style-type: none"> 1. First layer – spray evenly with sweeping motion and pressure of 2-4 bar until the proper coverage is obtained. The distance from the surface to be painted should be of 50cm. 2. Allow to flash off for 30÷50 minutes between coats. 3. In order to obtain the desired texture reduce the pressure and increase the distance from the surface to be painted. <p>To achieve fine texture, apply the second layer with a fine mist spray by reducing the pressure and material flow.</p> <p>The distance from the object and pressure change the created structure.</p>




TROTON Sp. z.o.o

	<p>Drying time</p> <p>Dust dry: 1 h/ 20°C (68°F) Touch dry - ready for assembly: 3 days/ 20°C (68°F) Through dry (severe conditions): 7 days/ 20°C (68°F)</p> <p>Temperatures below 20°C (68°F) significantly increase the hardening time.</p> <p>Baking</p> <p>In order to accelerate the physical drying time we recommend baking under a maximum temperature of 45°C (113°F) for 50-60 minutes. Before baking wait the appropriate evaporating time of 1,5 to 2 hours after application.</p> <p>ATTENTION! Baking does not accelerate the dry through time. It is recommended to wait 7 days to achieve total hardness of the coating (under severe conditions).</p>

APPLICATION PROCESS RANGERS black / tintable

Gravity feed spray gun

	<p>Proportion ratio:</p> <p>3:1 + 10÷20% thinner for acrylic systems TROTON</p> <p>By volume: 600ml+200ml+ 80÷160ml By weight: 803g+243g+91÷183g</p> <p>Shake the product before opening. Open the lid, add hardener and close. Shake very well. Add thinner and shake again until all elements have been incorporated.</p>
---	---

	<p>Pot life about 1 h at 20°C (68°F)</p>
	<p>Number of layers 2 layers. 1 dry layer of approx. 50µm</p> <p>Parameters for gravity feed gun Nozzle: 1,4÷2,5 mm; Inlet pressure: 2,0 bar.</p> <ol style="list-style-type: none"> 1. First layer – spray evenly with sweeping motion, pressure of 2 bar until the proper coverage is obtained. The distance from the surface to be painted should be of 40cm. 2. Allow to flash off for 30÷50 minutes between coats. 3. In order to obtain the desired texture reduce the pressure and increase the distance from the surface to be painted. <p>To achieve fine texture, apply the second layer with a fine mist spray by reducing the pressure and material flow.</p> <p>The distance from the object and pressure change the created structure.</p>
	<p>Drying time</p> <p>Dust dry: 1 h/ 20°C (68°F) Touch dry - ready for assembly: 3 days/ 20°C (68°F) Through dry (severe conditions): 7 days/ 20°C (68°F)</p> <p>Temperatures below 20°C (68°F) significantly increase the hardening time.</p> <p>Baking In order to accelerate the physical drying time we recommend baking under a maximum temperature of 45°C (113°F) for 50-60 minutes. Before baking wait the appropriate evaporating time of 1,5 to 2 hours after application.</p> <p>ATTENTION! Baking does not accelerate the dry through time. It is recommended to wait 7 days to achieve total hardness of the coating (under severe conditions).</p>

RANGERS tintable

Color can be added to the tintable Rangers version with the addition of diluting products (for the whole mixture)

TROTON Sp. z.o.o

- Acrylic basecoat toner- 5÷10%
- Acrylic basecoat- 10÷15%
- Acrylic topcoat- 10÷15%




RANGERS black / tintable

Rangers can be over coated. Wait 24 hours for the product to dry. Abrade surface with Troton's fine unwoven abrasive fabric, clean and degrease (Silicone Remover Troton).

Anti-slip additive

To create a non slip surface add TROTON RANGERS anti-slip additive powder(10g).

1. Packaging contains 10g of anti-slip additive needed to fill one bottle of RANGERS protective coating (800ml mixture).
2. Pour the contents directly into the RANGERS bottle, add hardener and shake very well for about 2 minutes.
3. A non slip surface can be achieved by using an UBS or conventional gun. The anti-slip additive can be added to all layers or only to the last one.

	APPLICATION	
	UBS	Conventional gun
		
Proportion ratio	3:1	3:1+10÷20%
nozzle	-	1.4÷2.5 mm
		
Inlet pressure	2÷4 bar	2 bar
Distance	20÷50 cm	20÷50 cm
Number of layers	2	2
Flash off between layers	30÷50 minut	30÷50 minut
		
Ready for assembly	3 days	3 days
Through dry (severe conditions)	7 days	7 days
Efficiency	2,5÷3 m ²	3,5÷6,5 m ²

GENERAL NOTES

✓ D

do not exceed recommended doses

of hardener!

- ✓ Using such clear coats remember to spray first the edges and cavities and leave the front surfaces for the last stage of application. Thus we can avoid superfluous dust creation and achieve a smooth finish.

TROTON Sp. z.o.o

Address: Ząbrowo 14A, 78-120 Gościno, Poland, Tel: +48 94 35 123 94
Tel/Fax: +48 94 35 126 22 Website: www.troton.com.pl Email: troton@troton.com.pl

- ✓ Best results of application are achieved when using a professional baking booth, or when varnishing in a room specially suited for this goal with room temperature of 20°C / 68°F .
- ✓ Room temperature and the temperature of the product should be the same.
- ✓ When working with 2K products, clean guns and equipment immediately after use.
- ✓ The rooms should be well ventilated.

STORAGE

Store the product components in temperatures of 15 to 25°C (59 to 77°F), in a sealed container, in dry and cool places, away from fire and heat sources, as well as direct sunlight.

Note:

1. *Immediately close the tins after each use!*
2. *Protect hardener against freeze and humidity!*

WARRANTY PERIOD

RANGERS 3:1 – 12 months from the production date.

Hardener 1:3 for RANGERS - 12 months from the production date.

ZERO VOC Thinners - 12 months from the production date.

Important Information:

The information contained in this document corresponds to our present knowledge and is a guide to our products and their uses.

Read all directions and warnings prior to using Troton products - Safety Data Sheets can be found online at www.troton.com.pl or will be sent according to your request: troton@troton.com.pl

Technical Information: The technical information, recommendations and other statements contained in this document are based upon tests or experience that Troton believes are reliable, but the accuracy or completeness of such information is not guaranteed.

Many factors beyond Troton's control and uniquely within user's knowledge and control can affect the use and performance of a Troton product in a particular application. Given the variety of factors that can affect the use and performance of a Troton product, user is solely responsible for evaluating the Troton product and determining whether it is fit for a particular purpose and suitable for user's method of application.

Limitation of Liability: Except where prohibited by law, Troton will not be liable for any loss or damage arising from the Troton product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.

If used as instructed, this product is designed to comply with the European Volatile Organic Compound (VOC) Emission Standard for Automotive Refinish Coatings. Confirm compliance with your country, state and local air quality rules before use. The data on this sheet represent typical values. Since application variables are a major factor in product performance, this information should serve only as a general guide. Troton assumes no obligation or liability for use of this information.